


- 1 來自100% 純木漿的Formocel，台灣台化公司以高濕係數技術自行開發Formocel 類溶劑粘膠《符合 ISO 2076 品質標準》，是一種天然健康之環保無原纖維化纖維，織品透氣排濕性佳，具有絲綢般之光澤，高柔軟、高染色性及自然生物分解特性。其纖維特色為截面形狀為圓形，可表現出類似 Lyocell 的高質感，使織品手感舒適、柔順平滑如絲，色彩艷麗，尺寸安定性佳及具有優異的懸垂性，Formocel 的質感可創造時尚及流行，為高級舒適流行之綠色環保衣著用料。
- 2 適用於高級衣用面料，貼身衣物，吸濕發熱內衣、牛仔褲、裡襯用布、緹花面料與高級寢具用面料。

3 纖維物性：

項目/單位	品質
乾強度 (cN/dtex)	3.75 +/- 0.22
乾伸率 (%)	17.5 +/- 2.0
濕強度 (cN/dtex)	2.00 ↑
濕係數 (cN/dtex) / 5%	0.44 ↓


4 Formocel vs Lyocell 纖維截面形狀比較：



- 5 品質證明 (Quality certificates)
依中國SGS紡織製品質量監督檢驗中心認證為類 Lyocell 棉 (SGS Test Report No. HKSL1308167423TX)

6 專業代理

作為台化正式授權的 Formocel® 代理商，仁通實業和用家合作多年，質量穩定，價格優惠，歡迎訂購洽談。



Formocel Rayon Staple Fiber with Circular Cross –Section Developed by FCFC Excellent Substitution for Lyocell Fiber Compliance with standards of ISO 2076



- 1 "Formocel" fiber, made of pure wood pulp, has high soft feeling, good dyeability and biodegradability characteristics, of which fabrics is with brilliant luster, dimensional stability, excellent drape and no fibrillation. It is an environment friendly product for high class and comfortable hometextiles and apparel.
- 2 Suitable for high class clothes, underclothing, lining, warmth-retaining underclothing, summer shirts, sportswear, jeans wear, bedding fabrics, and upholstery fabrics.

3 Technical Specifications:

ITEM / UNIT	QUALITY
Tenacity, Cond (cN/dtex)	3.75 +/- 0.22
Elongation, Cond (%)	17.5 +/- 2.0
Tenacity, Wet (cN/dtex)	2.00 ↑
Wet Modulus (cN/dtex) /5%	0.44 ↑

4 Professional Agent

As the authorized official Formocel® agents, Ren Tong Industrial Limited have been cooperating with Formosa Chemicals and buyers for decades, we offer stable supply of high quality and competitive price, any enquires and consultations are highly welcome.

Hong Kong Headquarter

Rm2601-3, 26/F., CC Wu Building, 302-308 Hennessy Road, Wanchai, Hong Kong
Tel: (852)2833 9102 | 2833 9165, Fax: (852)2833 5697, Email: mail_hkg@rentong.com, Website: www.rentong.com

ShangHai Office
Tel: (86) 21-6233 2350
Fax: (86) 21-6233 6032

GuangZhou Office
Tel: (86) 20-2886 5838
Fax: (86) 20-2886 5836

TianJin Office
Tel: (86) 22-2333 6083
Fax: (86) 22-2333 6382